

Date: July 8, 2014
To: MAG Specifications and Details Committee
From: Brian Gallimore, Chairman MAG Materials Working Group
Subject: Revisions to Sections 325 & 717

Case #14-19

PURPOSE: Incorporate revisions to Section 325, "*PLACEMENT AND CONSTRUCTION OF ASPHALT-RUBBER ASPHALT CONCRETE*" and Section 717, "*ASPHALT-RUBBER ASPHALT CONCRETE*" into the MAG Specifications.

REVISIONS:

- 325.2.1 - Added provisions for terminal-blended asphalt-rubber binder (ARB). Also identified ARB design location within Section 717.
- 325.2.2 - Corrected wording to improve clarity. Section needs additional work to better address terminal-blend operations.
- 325.5 - Added and revised wording to improve clarity.
- 325.7.2 - Minor wording revisions.
- 325.7.3 - Correction of referenced Section number.
- 325.8 - Removed redundant wording and revised wording for clarity.
- 325.9.2 - Added wording to address additional means of performing acceptance testing to provide flexibility to agencies. Current specification is not workable for most agencies or for smaller project; e.g. City of Scottsdale.
 - 325.9.2.1 - This entire section needs reworking to allow sampling from the grade and testing of ARAC via ignition method.
 - 325.9.2.2 - This entire section needs reworking to allow sampling from the grade and testing of ARAC via ignition method and adding language for ignition calibration protocol.
 - 325.9.3.2.1 - This entire section needs discussion as some agencies have expressed concerns.
 - 325.9.3.2.2 - Removed reference limiting nuclear gauges to thin lift models. Review correlation language.
- 717.2.2 - Table 717-3 needs review to ensure it is in line with current local practice.
- 717.3.2 - Table 717-5 needs review to ensure it is in line with current local practice. Wording revised and/or added to improve clarity

SECTION 325

PLACEMENT AND CONSTRUCTION OF ASPHALT-RUBBER ASPHALT CONCRETE

325.1 DESCRIPTION:

Asphalt-rubber asphalt concrete (ARAC) consists of supplying, placing and compaction of plant-mixed, gap-graded ARAC over asphalt surfaces. The thickness of the finished ARAC overlay shall be within the range of one to two inches as shown on the plans or as specified in the special provisions.

325.2 MATERIALS:

ARAC shall consist of a mixture of aggregate, mineral admixture and asphalt-rubber binder (ARB) as specified in Section 717.

325.2.1 Mixing of Asphalt-Rubber Binder: Mixing of asphalt-rubber binder (ARB) may take place in a dedicated blending & storage unit connected to the hot plant or at the asphalt binder supplier terminal. In either case, the temperature of the asphalt cement shall be between 375° F and 425° F prior to the addition of crumb rubber. No agglomerations of crumb rubber particles in excess of 2 inches in the least dimension shall be allowed in the mixing chamber. The crumb rubber and asphalt cement shall be accurately proportioned in accordance with the ARB design, as identified in 717.2.1.4, and thoroughly mixed prior to the beginning of the one hour reaction period. Reaction time may be decreased to 45-minutes if documentation is provided that the physical properties of the mix design requirements are consistently met using a 45-minute reaction period. The Contractor or supplier shall document that the proportions are accurate and that the crumb rubber has been uniformly incorporated into the mixture. Additionally, the Contractor or supplier shall demonstrate that the crumb rubber particles have been thoroughly mixed into the base asphalt cement. The occurrence of crumb rubber floating on the surface or agglomerations of crumb rubber particles shall be evidence of insufficient mixing. The temperature of the ARB immediately after mixing shall be between 350° F and 400° F. Reaction time shall start after all of the material for the batch has been mixed and the minimum reaction temperature of 350° F has been achieved.

Prior to use, the viscosity of the ARB shall be tested by the use of a rotational viscometer, which is to be furnished by the Contractor or supplier. The Contractor or supplier shall provide a qualified person to perform the testing.

325.2.2 Handling of ARB: Once the ARB has been mixed, it shall be kept thoroughly agitated during periods of transport (if applicable) and use to prevent settling of the crumb rubber particles. During the production of ARAC the temperature of the ARB shall be maintained between 325° F (163°C) and 400° F (204°C). However, in no case shall the ARB be held for more than 10 hours at these temperatures. It shall not be allowed to cool to a temperature of 250° F (121°C) or less and held at that temperature for not more than four days. The process of cooling and reheating shall not be allowed more than one time for a batch of ARB.

For each load or batch of ARB, the Contractor or supplier shall provide the Engineer with the following documentation:

- (A) The source, grade, amount and temperature of the asphalt cement prior to the addition of crumb rubber.
- (B) The source, type and amount of crumb rubber and the rubber content expressed as percent by the weight of total ARB.
- (C) Times and dates of the crumb rubber additions, resultant viscosity test, and the elapsed reaction time at which the viscosity test was taken.
- (D) A record of the temperature, with time and date reference for each load or batch. The record shall begin at the time of the addition of crumb rubber and continue until the load or batch is completely used. Readings and recordings shall be made at every temperature change in excess of 20° F, and as needed to document other events which are significant to batch use and quality.

325.3 WEATHER AND MOISTURE CONDITIONS:

ARAC shall be placed only when the surface is dry, and when the atmospheric temperature in the shade is 55° F or higher. No ARAC shall be placed when the weather is foggy or rainy. ARAC shall be placed only when the Engineer determines other conditions are suitable.

Revised 2012

Comment [DL1]: I think the ARB language here is sufficient in that it mentions terminal blended ARB. It is also mentioned in 717.

Comment [DLC2]: May need additional language for terminal blended ARB.

SECTION 325

325.4 APPLICATION OF TACK COAT:

A tack coat shall be applied to all existing and to each new course of ARAC prior to the placing of a succeeding lift of ARAC. The tack coat may be deleted when a succeeding layer of ARAC is being applied over a freshly laid course that has been subjected to very little traffic when approved by the Engineer.

The application of the tack coat shall comply with Section 329. The grade of emulsified asphalt shall be SS-1h or CSS-1h as specified in Section 713.

The same material that is specified above for the tack coat shall be applied to the vertical surfaces of existing pavements, curbs, and gutters, against which asphalt concrete is to be placed.

The surface to be covered may require repair or patching as directed by the Engineer. This shall be addressed in the project specifications prior to the bidding of the project.

325.5 MIX PRODUCTION:

All materials shall be proportioned by weight in a hot mix asphalt plant in the proportions required by the mix design to provide a homogeneous and workable mass. Each hot mix asphalt plant shall be inspected in accordance with the provisions contained in the 'Hot Mix Asphalt Production Facilities' by the Arizona Rock Products Association and shall have a current inspection certificate. All measuring devices shall be calibrated at least annually by a technician licensed by the Arizona Bureau of Weights & Measures. Mixing plants shall conform to the requirements of AASHTO M-156, except as modified herein.

In drum mix plants the mineral admixture shall be added and thoroughly mixed with the mineral aggregate by means of a mechanical mixing device prior to the mineral aggregate and mineral admixture entering the dryer. The moisture content of the combined mineral aggregate shall be a minimum of three percent by weight of the aggregate during the mixing process.

For drum-mix plants, the mineral admixture shall be weighed across a weigh belt, or other approved alternative weighing system, with a weight totalizer prior to entry into the mechanical mixing device. The mechanical mixing device shall be a pugmill type mixer that is in good working condition. The rate of the aggregate feed shall not exceed the mixing device's capacity in ton per hour. The mixer shall be constructed to minimize the loss of mineral admixture and shall be located in the aggregate delivery system at a location where the mixed material can be readily inspected. The mixing device shall be capable of effective mixing in the full range of the ARAC production rates.

The hot plant and equipment shall be constructed and operated to prevent loss of mineral admixture through the dust collection system of the plant.

A positive signal system shall be provided and utilized during production whereby the mixing shall automatically be stopped if the mineral admixture is not introduced into the mineral aggregate. The plant will not be permitted to operate unless the signal system is in good working condition.

The introduction of ARB shall be controlled by an automated system fully integrated with the controls ~~or for~~ the mineral aggregate and mineral admixture. The production of the plant shall be controlled by the rate required to obtain a uniform mixture of all components. Drying and heating shall be accomplished in such a manner as to preclude the aggregate or mineral admixture from becoming coated with un-spent fuel. The completed ARAC may be held in storage for up to 12 hours in insulated or heated silos, providing the minimum temperature noted herein for placement and compaction is met behind the placement device. If the Engineer determines that there is an excessive amount of heat, heat loss, drain down, segregation and/or oxidation of the mixture due to temporary storage, use of surge bins or storage bins will be discontinued.

The temperature of the ARAC, with unmodified binders, upon discharge from the mixer shall not exceed 350° F. The discharge temperature may be increased, when approved by the Engineer. If the ARAC is discharged from the mixer into a hopper, the hopper shall be constructed so that segregation of the ARAC will be minimized.

Revised 2012

SECTION 325

325.6 TRANSPORTATION:

Petroleum distillates or other substances that will have a detrimental effect on the asphalt concrete shall not be used as a release agent.

The beds of all transportation units shall be clean and smooth to allow the free flow of material into the paving machine's hopper.

Tarpaulins shall be furnished on all trucks and used when weather condition warrant, or if directed by the Engineer.

325.7 PLACEMENT:

325.7.1 Surface Preparation:

Before placing ARAC on existing pavements, severely raveled areas or cracked areas that are depressed more than 3/4" from the adjoining pavement shall be cut out and patched at least 48 hours prior to the resurfacing operation. Over-asphalted (bleeding or flushing) areas or rough high spots shall be removed by burning or blading. Large shrinkage cracks shall be filled with asphalt sealing compound acceptable to the Engineer. The entire surface shall be cleaned with a power broom. Raveled areas that do not require removing shall be cleaned by hand brooming. The above surface cleaning requirements are included as part of the ARAC paving operations, and the cost thereof shall be included in the ARAC pay item. Pavement repairs and crack sealing when required are to be compensated for by other appropriate contract pay items.

Prior to placing the ARAC on milled surfaces, pot-holes left by the milling operation shall be repaired by the Contractor, as a related non-pay item and as required by the Engineer. The milled area shall be swept.

After surfaces have been prepared to the satisfaction of the Engineer, they shall receive a tack coat as specified in Section [325.4](#).

Traffic will not be permitted over surfaces which have received a tack coat. When the overlay is to extend onto a concrete surface, the concrete surface shall be thoroughly cleaned of loose dust and cement particles and shall be tack coated.

325.7.2 Placing and Construction Methods:

All courses of ARAC shall be placed and finished by means of a self-propelled paving machine equipped with an automatically actuated control system, except under certain conditions or at locations where the Engineer deems the use of a self-propelled paving machine impracticable.

The control system shall control the elevation of the screed at each end by controlling the elevation of one end directly and the other end indirectly either through controlling the transverse slope or alternatively when directed, by controlling the elevation of each end independently.

The control system shall be capable of working with one of the following devices:

- (A) Ski or non-contact device of not less than 30 feet in length, supported throughout its entire length
- (B) Taut stringline or wire set to grade
- (C) Short ski or sonar sensing units from curb control
- (D) Joint matching shoe


Failure of the control system to function properly shall be cause for the suspension of asphalt concrete production. In order to achieve a continuous operation, the speed of the paving machine shall be coordinated with the hot mix plant and transport units.

If the ARAC is dumped from the hauling vehicles directly into the paving machine, care shall be taken to avoid jarring the machine or moving it out of alignment. No vertical load shall be exerted on the paving machine by the truck.

If ARAC is dumped upon the surface being paved and subsequently loaded in the paving machine, the loading equipment shall be self-supporting and shall not exert any vertical load on the paving machine. Substantially all of the ARAC shall be picked up **and loaded into the paving machine.** If ARAC is placed in a windrow during paving, the windrow shall not exceed

SECTION 325

| a distance greater than 150 feet in front of the paving machine.



SECTION 325

~~and loaded into the paving machine. If ARAC is placed in a windrow during paving, the windrow shall not exceed a distance greater than 150 feet in front of the paving machine.~~

Self-propelled paving machines shall spread the mixture without segregation or tearing, true to line, grade and crown as indicated on the project plans. Pavers shall be equipped with hoppers and augers that will distribute the mixture uniformly in front of an adjustable floating screed. The raising of the hopper wings ~~must~~ shall be minimized and the paving machine shall not be operated when in an empty condition.

Screeds shall include any strike-off device operated by tamping or vibrating action which is effective, without tearing, shoving or gouging the mixture and which produces a course with a uniform texture and density for the full width being paved. Screeds shall be adjustable as to height and crown and shall be equipped with a controlled heating device for use when required. In the case of the screed, auger extensions and vibrators shall be installed wherever the screed is extended more than one (1) foot beyond the end of the base auger or auger extension. However, when placing material against an extremely uneven curb or edge over a short distance, the Engineer may waive the auger extensions and vibrators.

325.7.3 Compaction: It is the contractor's responsibility to perform any desired Quality Control monitoring and/or testing during compaction operations to achieve the required compaction. The temperature of the ARAC immediately behind the laydown machine shall be at least 275° F. A probe type electronic thermometer with a current calibration sticker attached will be used to measure the temperature of the asphalt concrete mixture. When measuring the temperature of the mat, the probe shall be inserted at mid-depth and as horizontal as possible to the mat. When the pavement lift is less than 1.5-inches, the temperature of the material shall be measured in the truck by inserting a calibrated probe type electronic thermometer, or other approved measuring device, to a point at least 6" below the surface of material.

Asphalt compaction equipment shall be of sufficient size and weight to accomplish the required compaction. All compaction equipment shall be operated and maintained in accordance with the manufacturer's recommendations and the project requirements. Pneumatic tired compactors shall not be used.

The Engineer will determine the acceptability of the pavement compaction in accordance with Section ~~325.10~~ 325.9. At any place not accessible to the roller, the mixture shall be thoroughly compacted with tampers to provide a uniform and smooth layer over the entire area compacted in this manner.

325.7.4 Lime Water: An application of lime water shall be applied by the Contractor to the compacted ARAC surface after final compaction, prior to opening the roadway to traffic, or when requested by the Engineer to cool the pavement to prevent tracking and pick-up. The lime water solution shall be applied at the rate of approximately ½ gallon/square yard. The lime shall be mixed using a minimum of one (1) 50-pound bag per 3,000 gallons of water.

325.7.5 Adjustments: After installation of an overlay course all necessary frame and cover adjustments for manholes, valve boxes, survey monuments, sewer clean-outs, etc., shall be completed by the Contractor within the given segments being surfaced.

On roads without curb and gutter, the existing shoulder elevation shall be adjusted by the Contractor to match the elevation at the edge of new overlay and slope away from the new pavement surface at a rate that the existing quantity of shoulder material will allow. Shoulder material includes the existing shoulder, millings, untreated base materials, or a granular material approved by the Engineer. Shoulder material shall be compacted to a minimum of 95% of maximum density, determined in accordance with Section 301.3.

325.8 QUALITY CONTROL:

It is the contractor's responsibility to perform Quality Control monitoring and/or testing during ARAC production to achieve the required compaction and ~~to perform Quality Control monitoring and/or testing during ARAC production to achieve~~ the required mix properties. The Engineer may obtain samples of any portion of any material at any point of the operations for his own use. Also, the Engineer may order that the use of any drying, proportioning ~~and/or~~ mixing equipment or the handling of any material be discontinued which, in his/her opinion, fails to produce a satisfactory mixture.

The ARAC produced shall conform to the requirements of the production tolerances established in Section 325.9. When the ARAC does not conform to the production tolerances, it shall be reported to the Engineer, and corrective quality control

SECTION 325

measures shall be implemented, or production shall cease immediately at no additional cost to the contracting Agency or Engineer.

325.9 ACCEPTANCE:

325.9.1 Acceptance Criteria: Unless otherwise specified, asphalt concrete will be divided into lots for the purpose of acceptance. A lot shall be considered to be one day's production. When the quantity of asphalt concrete placed in a day exceeds 500 tons but is less than 2000 tons, the lot shall be divided into 500 ton sublots or fraction thereof. Where the quantity of asphalt concrete placed in a day exceeds 2000 tons, the day's production will be divided into four (4) approximately equal sublots. A minimum of one sample will be obtained from each lot. Tests used to determine acceptance will be performed by the Engineer or a laboratory employed by the Engineer. In either case the laboratory shall be accredited by the AASHTO Accreditation Program (AAP), for the tests being performed. The acceptance laboratory will take representative samples of the asphalt concrete from each sublot to allow for gradation, binder content, air voids, pavement thickness and compaction of base and surface course. Each sublot will be accepted based upon the test data from the sample(s) from that sublot. All acceptance samples shall be taken using random locations or times designated by the Engineer in accordance with ASTM D3665. ~~Unless otherwise specified, ARAC will be divided into 500 ton increments for the purpose of acceptance. Generally, a minimum of one sample will be obtained from each 500 tons of production or fraction thereof for determination of binder content and gradation. Tests used to determine acceptance will be performed by the Engineer or a laboratory employed by the Engineer. In either case the laboratory shall be accredited by the AASHTO Accreditation Program (AAP), for the tests being performed. All acceptance samples shall be taken using random tonnages, locations or times as designated by the Engineer in accordance with ASTM D 3665. Acceptance testing results will be furnished to the contractor within five working days of receipt of samples by the acceptance laboratory.~~

Comment [DL3]: Inserted same sampling criteria and language as MAG 321.

325.9.2 Gradation and Binder Content and Air Voids: Acceptance testing for gradation and binder content will be performed in one of the following ways: A) Plant-based testing of the mineral aggregate and binder content using cold feed samples and a nuclear asphalt content gauge or B) End-product testing of the ARAC using an ignition furnace with the gradation being performed on the resulting aggregate. The specifics of these methods and the determination of Marshall air voids are detailed in the following subsections.

Formatted: Font: Not Bold

Formatted: Font: Not Bold

Formatted: Font: Not Bold

Formatted: Font: Not Bold

325.9.2.1 Plant-Based Sampling and Testing

325.9.2.1.1 Mineral Aggregate Gradation: The acceptance laboratory will take a sample of the mineral aggregate in For each approximate 500 tons of ARAC produced, at least one sample of mineral aggregate will be taken. Samples will be taken in accordance with the requirements of Arizona Test Method 105 on a random basis. For batch plants, the sample shall be taken from the hot bins. For plants other than batch plants, the sample shall be taken from the cold feed belt. Samples will be taken by means of a sampling device which is capable of obtaining representative samples. The device, which shall be approved by the Engineer, shall be furnished by the contractor. In any shift that the production of ARAC is less than 500 tons, at least one sample will be taken.

Samples will be tested for conformance with the mix design gradation, with or without mineral admixture as appropriate, in accordance with the requirements of Arizona Test Method 201.

During production, the allowable deviations from the mix design gradation targets are listed in Table 325-1 below. The allowable production tolerances may fall outside of the mix design gradation bands.

TABLE 325-1		
GRADATION ACCEPTANCE LIMITS FOR ASPHALT-RUBBER MIXES		
Sieve Size	1" & 1 1/2" Lift Thickness	2" Lift Thickness
1 inch	100%	100%
3/4 inch	100%	92-100%
1/2 inch	92-100%	±6%
3/8 inch	±6%	±6%
No. 4	±6%	±6%
No. 8	±6%	±6%

SECTION 325

No. 30	±4%	±4%
No. 200	±2%	±2%

If the results from a single acceptance sample fall outside of the acceptance limits in Table [325-1](#) a second sample shall be taken and if the second acceptance sample is also outside of the acceptance limits in Table [325-1](#) the Contractor shall cease production of asphalt concrete. Production shall not begin again until calibration test results verify that adjustments made to materials or proportions yield a gradation that falls within acceptance limits in Table [325-1](#).

325.9.2.1.22 Binder Content: During production of ARAC, the contractor shall maintain at the plant site a nuclear asphalt content gauge calibrated and operated in accordance with Arizona Test Method 421. At the discretion of the Engineer, the Owner may choose to prepare the calibration samples for use by the contractor. Under the observation of the Engineer, the contractor shall determine the ARB content by means of the nuclear asphalt content gauge a minimum of four times per full shift. The Engineer shall determine the times that the samples are taken. The contractor's technicians performing the testing, including the calibration of the nuclear gauge, shall meet the technician requirements given in the Arizona Department of Transportation (ADOT) System for the Evaluation of Testing Laboratories. The requirements may be obtained from ADOT Materials Group, 1221 North 21st Avenue, Phoenix, AZ 85009.

Comment [DLC4]: Need to add language detailing performing gradation on the aggregate obtained from ignition testing.

Comment [DL5]: This language in the paragraph below the table is nearly identical to the same subsection in 321. Since Don referenced plant and grade sampling above, I think this subsection is ok as is. I added a subsection for gradation and binder content on End-Product samples.



SECTION 325

Production of ARAC shall cease immediately and the plant and/or the nuclear asphalt content gauges re-calibrated if any single test result varies by an amount greater than $\pm 0.60\%$, or the average of three consecutive test results varies by an amount greater than $\pm 0.40\%$, from the mix design target. Material that has already been produced may be used on the project if the single test value representative of that material varies by an amount from $\pm 0.61\%$ to $\pm 0.75\%$, inclusive, from the mix design target. Material that has already been produced may not be used on the project if the single test value representative of that material varies by an amount greater than $\pm 0.75\%$ from the mix design target unless, by retesting, the material is found to be acceptable.

When there is cause to question the ARB content being obtained via nuclear asphalt content gauge, or if approved by the Engineer, the ARB content may be determined using inventory data provided by the supplier as detailed in the following paragraphs. This will only apply for plants providing ARAC exclusively for the subject project or if an asphalt cement tank is dedicated for the shift of ARAC production.

The determination of the actual ARB content by inventory methods may include weighing of asphalt cement deliveries, invoice quantities, volumetric tank measurements using a calibrated rod (tank stickings) corrected for temperature, computerized mass-flow meter, and accounting for wasted materials. If a computerized mass-flow meter is used, documentation of its calibration shall be submitted to the Engineer prior to ARAC production. At any time during ARAC production, the Engineer may require that a new calibration of the mass-flow meter be performed.

If there is a difference of greater than 0.2% ARB between the ARB content measured by nuclear asphalt content gauge testing and the actual ARB content as determined by inventory, the contractor may request that the ARB content be determined by inventory. The contractor must make such a request in writing within two working days after receiving the test results for the first day of ARAC production.

325.9.2.2 End Product Sampling and Testing

325.9.2.2.1 Mineral Aggregate Gradation and Binder Content: The acceptance laboratory will take a sample of the asphalt concrete in accordance with the requirements of Section 2 or 4 of Arizona Test Methods 104 or AASHTO T-168 from each subplot. The minimum weight of the sample shall be 45 pounds. Asphalt binder content and gradation shall be determined in accordance with AASHTO T-308 using the ignition furnace for each subplot. The acceptance laboratory is responsible for obtaining the necessary materials and performing an ignition furnace calibration as outlined in AASHTO T-308 for each asphalt concrete mixture utilized on the project. The correction factor used for each test shall be clearly indicated on the report.

During production, the allowable deviations from the mix design gradation targets are listed in Table 325-1 above. The allowable production tolerances may fall outside of the mix design gradation bands.

If the results from a single acceptance sample fall outside of the acceptance limits in Table 325-1 a second sample shall be taken and if the second acceptance sample is also outside of the acceptance limits in Table 325-1 the Contractor shall cease production of asphalt concrete. Production shall not begin again until calibration test results verify that adjustments made to materials or proportions yield a gradation that falls within acceptance limits in Table 325-1.

If the asphalt binder content is within $\pm 0.60\%$ of the mix design target value, the asphalt concrete will be paid for at the contract unit price. If the asphalt binder content deviates by more than $\pm 0.60\%$ from the mix design target value, the deficient area will be evaluated within the subplot by coring at maximum intervals of 100 feet from the deficient sample. The asphalt content of the original deficient sample will be averaged with the asphalt binder content of the cores taken for re-evaluation to determine compliance with the acceptance requirements. If the resulting average of the asphalt binder content deviates by more than $\pm 0.60\%$ from the mix design target value, then Table 325-2 shall apply to the subplot. Additional cores may be required to define the limits of the deficient area, and shall not be used for re-evaluating acceptance.

Comment [DL6]: The gradation table is the same no matter which sampling method. Therefore, instead of adding the same table again, I just referenced the table above.

Comment [DL7]: Because grade samples will usually be tested after completion of the day's production, a payment table will probably need to be included for binder content. Because of the inherent issues with sampling and testing binder content on ARAC mixes, we would propose a allowable deviation of $\pm 0.60\%$ from the mix design target. The payment schedule would be similar to that found in section 321, with changes to the deviation column reflecting the $\pm 0.60\%$ value instead of the $\pm 0.40\%$ value shown in section 321.

TABLE 325-2	
ASPHALT BINDER CONTENT ACCEPTANCE AND PENALTIES	
<u>Deviation from that permitted</u>	<u>(\$ per ton of asphalt concrete)</u>
<u>Over 0.2% above that permitted</u>	<u>Removal* or EA</u>

SECTION 325

Over 0.1% to 0.2% above that permitted	\$6.00
Over 0.0% to 0.1% above that permitted	\$2.00
Within permitted range	Full Payment
Over 0.0% to 0.1% below that permitted	\$2.00
Over 0.1% to 0.2% below that permitted	\$6.00
Over 0.2% below that permitted	Removal* or EA

Comment [DL8]: I inserted one table, same language as 321-4A where the contracting agency is the owner. Do we need a second table for Permits? It seems like 99% of the ARAC is for jobs for the agencies.

NOTES: *The Contractor shall remove and replace the entire subplot that is deficient.
 EA = Engineering Analysis per Section 325.9.4

325.9.2.3 Marshall Air Voids: For purposes of determining Marshall air voids, the acceptance laboratory will ~~take designate~~ one sample of the ARAC in accordance with the requirements of Section 2(h) of Arizona Test Methods 104 or AASHTO T-168 for each day's production or as directed by the Engineer's. The minimum weight of the sample shall be 45 pounds. The bulk density shall be tested in accordance with AASHTO T-245. The maximum theoretical density shall be tested in accordance with the requirements of AASHTO T-209, including fan drying per AASHTO T-209 Section 11. Effective voids determined on the laboratory compacted specimens will be determined in accordance with the requirements of AASHTO T-269. Should the testing for effective air voids not meet the "Full Payment" or "No Corrective Action" requirements of Table ~~325-23~~, additional testing for laboratory air voids on additional samples will be performed as necessary to determine the extent of the deficiency.

Comment [DL9]: Air voids are tested the same whether the sample was from the plant or the grade, so I modified the numbering system slightly so that gradation and binder content were broken out depending on the sample source but voids are now in their own little subsection.

TABLE 325-32		
LABORATORY VOIDS ACCEPTANCE AND PENALTIES		
Marshall Air Voids (Measured at 75 blows) Deviation from Mix Design Target	When the contracting agency is the owner: Payment Reduction (\$ per ton of asphalt concrete)	When the contracting agency is not the owner (i.e. permits): Corrective Action
± 0% to 2.0%	Full Payment	No corrective action
± 2.1% to 2.9%	\$1.00	EA (see 325.9.5+10.6)
± 3.0% to 4.0%	\$2.50	EA (see 325.9.5+10.6)
± Greater than 4.0%	Removal* or EA per 325.10.4	Removal* or EA per 325.9.5+10.4

325.9.4.3 Density: The temperature of ARAC just prior to compaction shall be at least 275° F. The Engineer may change the rolling procedure if in the Engineer's judgment the change is necessary to prevent picking up of the ARAC.

325.9.4.3.1 Equipment: Asphalt compaction equipment shall be of sufficient size and weight to accomplish the required compaction. All compaction equipment shall be operated and maintained in accordance with the manufacturer's recommendations and the project requirements. The compactors shall be self-propelled and shall be operated with the drive wheel in the forward position. The compactors shall weigh not less than eight tons. Compactors shall not be used in the vibratory mode for courses of one inch or less in nominal thickness. The wheels of compactors shall be wetted with water, or if necessary soapy water, or a product approved by the Engineer to prevent the ARAC from sticking to the steel wheels rolling.

Revised 2012

SECTION 325

325.9.43.2 Compaction Procedures

325.9.43.2.1 Pavement Lift Thickness 1 ½ Inches or Less: A minimum of three static steel-wheel compactors shall be provided; however, sufficient compactors must be provided so that the drums of the compactors when staggered will cover the entire width of the paving machine on the initial forward pass while a static compactor remains to complete final rolling. The roller(s) for final compaction shall follow as closely behind the initial breakdown as practical, such that a uniformly smooth surface is achieved. As many passes as are possible shall be made with the compactors before the temperature of the ARAC falls below 220° F.

Achieving the required compaction is the responsibility of the contractor. The number and types of rollers is the contractor's responsibility and shall be sufficient to meet these requirements.

325.9.43.2.2 Pavement Lift Thickness Greater than 1 ½ Inches: Achieving the required compaction is the responsibility of the contractor. The number and types of rollers is the contractor's responsibility and shall be sufficient to meet these requirements. Initial breakdown rollers shall follow as closely behind the paving machine as practical. The roller(s) for final compaction shall follow as closely behind the initial breakdown as practical, such that a uniformly smooth surface is achieved.

Compaction will be determined using a correlated ~~thin lift~~ nuclear density gauge and will be monitored for acceptability continuously during construction. The density of the compacted mixture shall not be less than 95% of the laboratory unit weight composed of the same mixture compacted by the 75 blow method of AASHTO T-245 at the job mix design specified compaction temperature. The outside one foot of each pass of the pavement course or any unconfined edge will be excluded from testing. The Engineer may exclude areas from the compaction lot that are not accessible by normal compaction equipment.

Nuclear Density Gauge Correlation - During placement of the test strip or on the first day of paving, the pavement surface shall be tested with a ~~thin lift~~ nuclear density gauge at a minimum of four locations. These same locations shall then be cored, using a 4-inch diameter core barrel, and tested for bulk density (AASHTO T-166A, or T-275) and a correlation value developed between the nuclear density gauge and the asphalt cores.

325.9.43.3 Compacting Miscellaneous Items and Surfaces: ARAC used in the construction of miscellaneous items and surfaces shall be compacted using compactors, hot-hand tampers, smoothing irons, mechanical vibrating hand tampers, or with other devices to the extent considered necessary by the Engineer.

325.9.54 Engineering Analysis (EA): Within 10 working days after receiving notice that a lot or sublot of ARAC is deficient and is found to fall within the "Removal or EA" band per Table(s) ~~325-2 or 325-3~~, the contractor may submit a written proposal (Engineering Analysis) to accept the material in place at the applicable penalties along with possible remediation(s) listed in the "Removal or EA" category. An Engineering Analysis can also be proposed for non-removal categories of "Corrective actions" when the contracting agency is not the owner (i.e. permits).

The Engineering Analysis shall contain an analysis of the anticipated performance of the ARAC if left in place. The Engineering Analysis shall also detail the effect of any proposed corrective action to the material(s) in place as it relates to the in-place material's performance. The Engineering Analysis shall be performed by a professional engineer experienced in asphalt concrete testing and mix designs. If the lot or sublot is submitted for referee testing by the contractor, the ten working days allowed to prepare an engineering analysis will begin upon notification of referee test results.

When an Engineering Analysis recommends that a specific lot or sublot should not be removed, the Engineering Analysis will recommend that the following penalties (Table ~~325-34~~) be paid when the contracting agency is the owner, for the specific criteria being reviewed by the EA.

Comment [DLC10]: This section needs discussion. May want to review COP approach.

Formatted: Highlight

Comment [DL11]: Per DLC's comment above, this is the City's language.

Comment [DLC12]: Good correlation language for other sections.

TABLE 325-~~43~~

ENGINEERING ANALYSIS PENALTIES for REMOVAL* LOTS/SUBLOTS LEFT IN-PLACE


Acceptance Criteria	Acceptance Limits	Penalty When Contracting Agency is the Owner (\$/Ton)
---------------------	-------------------	---

SECTION 325

Laboratory Air Voids (Measured at 75 blows)	Deviation from Target Greater Than $\pm 4.0\%$	\$3.75
---	--	--------



Revised 2012



SECTION 325

Within 15 working days, the Engineer will determine whether or not to accept the contractor's proposed Engineering Analysis.

325.10 REFEREE:

In the event the contractor elects to question the acceptance test results for laboratory air voids, the Contractor may make a written request for additional testing of the affected material. Any request for referee testing must describe the contractor's reasons for questioning the validity of the original acceptance results and must clearly describe which set of acceptance tests are in question. The Contractor will engage an independent laboratory (at the Contractor's own expense) who is accredited by AAP in all of the acceptance test methods. The independent laboratory shall be acceptable to the Engineer and shall perform a new set of acceptance tests as required by Section [325.9.2.3](#) representing the area or set of tests in question. The results of these determinations will be binding on both the contractor and the agency.

These tests will include Marshall unit weight, maximum theoretical unit weight, and laboratory air voids. Samples for referee testing shall come from representative samples obtained from the completed pavement, as directed by the Engineer.

The number of samples taken will be the same as specified in Section [325.9.2.3](#). The independent laboratory shall compile the test results and transmit them to both the Engineer and the contractor. The independent laboratory shall include a report signed by an Engineer registered in the State of Arizona, who is experienced in asphalt concrete testing and mix design development. The signed report shall give an opinion that the material evaluated either does or does not comply with project specifications, shall clearly describe any deficiencies, and the results will be binding between all parties.

325.11 MEASUREMENT:

ARAC shall be measured by the ton, for the mixture actually used, which shall include the required quantities of mineral aggregates, filler material, asphalt-rubber binder and admixture.

Application of Lime Water shall be measured by the square yard. The measured area shall be the area of ARAC pavement to which the lime water is applied. The measured area shall only be counted one time regardless of the number of applications applied to the ARAC pavement section.

Shoulder adjustment to match the new pavement surface elevation shall not be measured. The cost of this work shall be included in the price paid for ARAC or other related pay items.

325.12 PAYMENT:

Payment for Asphalt Milling will be as specified in Section [317](#).

Payment for tack coat will be by the ton diluted, based on the rate of application, as directed by the Engineer.

Payment for ARAC will be at the contract unit price, complete in place.

Application of Lime Water as approved by the Engineer will be paid at the contract unit price.

Payment for frame and cover adjustments will be at the contract unit prices specified in the proposal.

- End of Section -

SECTION 717

ASPHALT-RUBBER ASPHALT CONCRETE

717.1 DESCRIPTION:

The work under this section shall consist of furnishing, proportioning and mixing all the ingredients necessary to produce an asphalt-rubber Asphalt Concrete (ARAC) material. ARAC mixes may be used for low or high traffic conditions, as determined by the agency. Low traffic conditions are conditions where the asphalt mix will be subject to low volume and low weight vehicle usage. Examples of this condition are residential streets, most parking lots and residential minor collector streets. High traffic conditions are conditions where the asphalt mix will be subject to high volume and/or heavy weight vehicle usage as found on major collector, arterial and commercial streets. Street classifications (i.e. minor collector and major collector) shall be determined by the specifying agency.

717.2 MATERIALS:

717.2.1 Asphalt-Rubber Binder (ARB):

Comment [DL1]: Insert language here regarding on-site ARB plant blending as well as off-site terminal blending?

717.2.1.1 Asphalt Cement: Asphalt cement shall conform to the requirements of Section 711.

717.2.1.2 Crumb Rubber: Crumb Rubber shall meet the gradation requirements as shown in Table 717-1 below when tested in accordance with Arizona Test Method 714.

TABLE 717-1	
GRADATION REQUIREMENTS OF CRUMB RUBBER	
Sieve Size	Percent Passing
	Type B
2.36 mm (#8)	
2.00 mm (#10)	100
1.18 mm (#16)	65 - 100
600 µm (#30)	20 - 100
300 µm (#50)	0 - 45
75 µm (#200)	0 - 5

The crumb rubber shall have a specific gravity of 1.15 ± 0.05 and shall be free of wire or other contaminating materials, and shall contain not more than 0.5 percent fabric. Calcium carbonate, up to four percent by weight of the crumb rubber, may be added to prevent the particles from sticking together.

Certificates of Compliance conforming to Arizona State Department of Transportation Standard Specifications for Road and Bridge Construction Section 106.05 shall be submitted. In addition, the Certificates shall confirm that the rubber is a crumb rubber, derived from processing at ambient temperature, whole scrap tires or shredded tire materials; and the tires from which the crumb rubber is produced is taken from automobiles, trucks, or other equipment owned and operated in the United States. The Certificates shall also verify that the processing does not produce, as a waste product, casings or other round tire material that can hold water when stored or disposed of above the ground. The crumb rubber to be used in asphalt-rubber binder shall be the type produced through a process of mechanical grinding at ambient temperature. Use of crumb rubber granules produced from a cryogenic process is prohibited.

717.2.1.3 Asphalt-Rubber Proportions and Properties: Ground crumb rubber in ARB shall be a minimum of 18 percent by weight of total binder,

ARB shall be Type 1 unless otherwise specified and conform to the requirements of Table 717-2 below:

SECTION 717

TABLE 717-2			
PHYSICAL PROPERTIES OF ASPHALT RUBBER BINDER			
Property	Requirement		
	Type 1	Type 2	Type 3
Grade of base asphalt cement	PG 64-16	PG 58-22	PG 52-28
Rotational Viscosity*; 350° F, Pascal seconds	1.5-4.0	1.5-4.0	1.5-4.0
Penetration; 39° F (4° C), 200g, 60 sec. (ASTM D5); dmm, min	10	15	25
Softening Point; (ASTM D36); °F, min.	135	130	125
Resilience; 77°F (ASTM D3407); %,min	25	20	15

* The Viscometer used must be a hand held rotational viscometer, such as a Rion (formerly Haake) Model VT – 04, or an equivalent, using Rotor No. 1. The rotor, while in the off position, shall be completely immersed in the binder at a temperature from 350° to 355° F for a minimum heat equilibrium period of 60 seconds, and an average viscosity determined from three separate constant readings (± 0.5 pascal-seconds) taken within a 30 second time frame with the viscotester level during testing and turned off between readings. Continuous rotation of the rotor may cause thinning of the material immediately in contact with the rotor, resulting in erroneous results.

717.2.1.4 Asphalt-Rubber Binder Design: At least two weeks prior to paving, the Contractor shall submit an ARB design prepared by an ADOT approved laboratory. Such design shall meet the requirements specified herein. The design shall show the values obtained from the required tests, along with the following information: percent, grade and source of the asphalt cement used; and percent, gradation and source(s) of the crumb rubber used, as well as the ARB blending location: on-site or terminal blended.

717.2.2 Aggregate: Coarse and fine aggregates shall conform to the applicable requirements of Tables 717-3 and 717-4 below. Coarse mineral aggregate shall consist of crushed gravel, crushed rock, or other approved inert material with similar characteristics, or a combination thereof, conforming to the requirements of these specifications.

Coarse aggregate is material retained above the Number 8 sieve and fine aggregate is material passing the Number 8 sieve. Aggregates shall be free of deleterious materials, clay balls, and adhering films or other material that prevent thorough coating with the asphalt cement. Mineral aggregate shall conform to the following requirements when tested in accordance with the applicable test methods.

TABLE 717-3		
MIX DESIGN GRADATION REQUIREMENTS		
Overlay Thickness	1" & 1- 1/2"	2"
Sieve Size	Percent Passing	Percent Passing
1" (25 mm)	100	100
3/4" (19 mm)	100	95-100
1/2" (12.5 mm)	95-100	78-92
3/8" (9.5 mm)	78-92	61-75
No. 4 (4.75 mm)	28-45	30-40
No. 8 (2.36 mm)	15-25	15-25
No. 30 (600 µm)	5-15	5-15
No. 200 (75 µm)	3.0-7.0	2.0-6.0

Comment [DLC2]: Need to review this table and compare to current practice.

The combined aggregate properties shall conform to the requirements of Table 717-4 below.

SECTION 717

TABLE 717-4 COARSE/FINE AGGREGATE REQUIREMENTS		
Characteristics	Test Method	Requirements
Fractured Faces, % (Plus No. 8)	ARIZ-212	85, 1 fracture 80, 2 or more
Uncompacted Voids, %	ARIZ-247	45.0 (High Traffic Volume) 42.0 (Low Traffic Volume)
Sand Equivalent (Minus No. 4)	AASHTO T-176	65 minimum
Plasticity Index	AASHTO T-89 & T-90	Non Plastic
L.A. Abrasion, % Loss	AASHTO T-96	9 max. @ 100 Rev. 40 max. @ 500 Rev.
Combined Bulk Specific Gravity	AI MS-2	2.35-2.85
Combined Water Absorption, %	AI MS-2	0-2.5

717.2.3 Mineral Admixture: Mineral admixture used in ARAC shall be dry hydrated lime conforming to the requirements of ASTM C1097 or Portland cement conforming to ASTM C150 for Type II, or ASTM C595 for Type IP. The minimum mineral admixture content will be 1.0percent, by weight of total aggregate.

717.3 MIX DESIGN REQUIREMENT:

717.3.1 General: The mix design for ARAC shall be prepared by a laboratory that is accredited through the AASHTO Accreditation Program (AAP) in Hot Mix Asphalt Aggregates and Hot Mix Asphalt. The laboratory shall be under the direct supervision of a Civil Engineer, registered by the State of Arizona, and who is listed by ADOT as a “Qualified Asphalt Concrete Mix Design Engineer” within ADOT’s latest list of approved laboratories. The latest list of approved laboratories is available on ADOT’s web page: http://www.azdot.gov/highways/materials/quality_assurance.asp.

The date of the design shall not be older than two years from the date of submittal, unless supportive documentation is provided and approved by the Engineer.

The mix design method used shall be in accordance with the Marshall Mix procedure, 75 blows, as described in Arizona Test Method 832 “Marshall Mix Design Method for Asphaltic Concrete (Asphalt Rubber) [AR-AC]”. Mix designs are subject to approval by the Engineer.

717.3.2 Mix Design Criteria: The mix shall comply with the criteria in Table 717-5 below.

TABLE 717-5 MARSHALL MIX DESIGN CRITERIA		
Criteria	Low Volume Traffic	High Volume Traffic
Asphalt Rubber Binder Content		
1” and 1-1/2” Overlay Thickness	8.4% minimum	8.0% minimum
2” Overlay Thickness	N/A	7.0% minimum
Mixture Air Voids, %	3.5-4.5	4.5-5.5
Voids in Mineral Aggregate, %	19.0 min	19.0 min
Tensile Strength Ratio, AASHTO T-283	65% minimum	65% minimum
Marshall Stability, pounds minimum	800	800
Marshall Flow, 0.01 inch minimum	16	16

Comment [DLC3]: Need to revisit this table as well.

The mix design report shall include the following elements as a minimum.

- (1) The name and address of the testing organization and the person responsible for the mix design report.
- (2) The mix plant identification and/or location, as well as the supplier or producer name.
- (3) The traffic condition (low or high traffic) and lift thickness.
- (4) A description of all products that are incorporated in the ARAC along with the sources of all products, including asphalt binder, crumb rubber, mineral aggregate, and admixtures.

SECTION 717

(5) The results of all testing, determinations, etc., such as: specific gravity and gradation, water absorption, sand equivalent, loss on abrasion, fractured coarse aggregate particles, Tensile Strength Ratio (AASHTO T-283), Marshall bulk density, stability and flow, asphalt absorption, percent air voids, voids in mineral aggregate. Historical abrasion values may be supplied on existing sources. The submittal should include a plot of the gradation on the Federal Highway Administration's 0.45 Power Gradation Chart and plots of the compaction curves.

(6) The laboratory mixing and compaction temperature ranges for the supplier and grade of asphalt-rubber binder used within the mix design.

(7) A specific recommendation for design ARB content and any limiting conditions that may be associated with the use of the design, such as minimum percentages of crushed or washed fine aggregate.

(8) The supplier's product code, the laboratory Engineer's seal (signed and dated), and the date the design was completed.

(9) The ARB blend-binder design.

The mix design shall be submitted to the Agency or Engineer by the Contractor/Supplier for which it was developed as part of his project submittals. Once the mix design has been approved by the agency or Engineer, the Contractor and/or his supplier shall not change plants nor utilize additional mixing plants without prior approval of the Engineer. Any changes in the plant operation, the producer's pit, the asphalt binder, including modifiers in the asphalt binder, or any other item that will cause an adjustment in the mix, shall be justification for a new mix design to be submitted.

- End of Section -