

Arizona Residential Post-Tensioned Round Table  
March 2007

**Recommendations for Standards of Construction  
and Design #1**

**SPECIAL INSPECTION**

The requirements for special inspection of concrete construction are provided in International Building Code 2003, Section 1704.4. Table 1704.4 lists 10 different inspection items for concrete construction. Six of the items (Numbers 1, 4, 5, 6, 8, and 10) could be applied to post-tensioned slabs on ground. The Arizona Residential Post-Tensioned Round Table makes the following recommendations for special inspection of residential post-tensioned slabs-on-ground.

1. Inspection of reinforcing steel, including pre-stressing tendons and placement shall occur prior to slab pour.
4. Verifying use of required design mix shall occur periodically.
5. At the time fresh concrete is sampled to fabricate specimens for strength tests, perform slump tests, and determine the temperature of the concrete.
6. Inspection of concrete placement for proper application and techniques shall occur for the full duration of concrete placement.
8. Verification of pre-stressing forces shall occur at the time of pre-stress application.
10. Prior to stressing of tendons in post-tensioned concrete, periodic verification of in-situ strength shall be performed per ACI 228.

The recommendations listed above satisfy the intent of the code.

The information presented for Recommendations for Standards of Construction and Design and its interpretation is only advisory. Please consult your local municipality, building official and/or your Structural Engineer of Record. They shall have the authority to adopt policies and procedures in order to change or clarify the aforementioned recommendations. Any changes or interpretations should be validated by written documentation.

Please see Appendix A, Recommendations for Standards of Construction and Design #1 for table 1704.4

**1704.3.3.3 Continuous monitoring.** Monitoring of bolt installation for pretensioning using the calibrated wrench method or the turn-of-nut method without matchmarking shall be performed on a continuous basis.

**1704.4 Concrete construction.** The special inspections and verifications for concrete construction shall be as required by this section and Table 1704.4.

**Exception:** Special inspections shall not be required for:

1. Isolated spread concrete footings of buildings three stories or less in height that are fully supported on earth or rock.
2. Continuous concrete footings supporting walls of buildings three stories or less in height that are fully supported on earth or rock where:
  - 2.1. The footings support walls of light frame construction;
  - 2.2. The footings are designed in accordance with Table 1805.4.2; or

2.3. The structural design is based on a  $f_c$  no greater than 2,500 pounds per square inch (psi) (17.2 Mpa).

3. Nonstructural concrete slabs supported directly on the ground, including prestressed slabs on grade, where the effective prestress in the concrete is less than 150 psi (1.03 Mpa).

4. Concrete foundation walls constructed in accordance with Table 1805.5(1), 1805.5(2), 1805.5(3) or 1805.5(4).

5. Concrete patios, driveways and sidewalks, on grade.

**1704.4.1 Materials.** In the absence of sufficient data or documentation providing evidence of conformance to quality standards for materials in Chapter 3 of ACI 318, the building official shall require testing of materials in accordance with the appropriate standards and criteria for the material in Chapter 3 of ACI 318. Weldability of reinforcement, except that which conforms to ASTM A 706, shall be determined in accordance with the requirements of Section 1903.5.2.

TABLE 1704.4  
REQUIRED VERIFICATION AND INSPECTION OF CONCRETE CONSTRUCTION

VERIFICATION AND INSPECTION	CONTINUOUS	PERIODIC	REFERENCED STANDARD <sup>a</sup>	IBC REFERENCE
1. Inspection of reinforcing steel, including prestressing tendons, and placement.	—	X	ACI 318: 3.5, 7.1-7.7	1903.5, 1907.1, 1907.7, 1914.4
2. Inspection of reinforcing steel welding in accordance with Table 1704.3, Item 5B.	—	—	AWS D1.4 ACI 318: 3.5.2	1903.5.2
3. Inspect bolts to be installed in concrete prior to and during placement of concrete where allowable loads have been increased.	X	—	—	1912.5
4. Verifying use of required design mix.	—	X	ACI 318: Ch. 4, 5.2-5.4	1904, 1905.2-1905.4, 1914.2, 1914.3
5. At the time fresh concrete is sampled to fabricate specimens for strength tests, perform slump and air content tests, and determine the temperature of the concrete.	X	—	ASTM C 172 ASTM C 31 ACI 318: 5.6, 5.8	1905.6, 1914.10
6. Inspection of concrete and shotcrete placement for proper application techniques.	X	—	ACI 318: 5.9, 5.10	1905.9, 1905.10, 1914.6, 1914.7, 1914.8
7. Inspection for maintenance of specified curing temperature and techniques.	—	X	ACI 318: 5.11-5.13	1905.11, 1905.13, 1914.9
8. Inspection of prestressed concrete: a. Application of prestressing forces. b. Grouting of bonded prestressing tendons in the seismic-force-resisting system.	X X	—	ACI 318: 18.20 ACI 318: 18.18.4	—
9. Erection of precast concrete members.	—	X	ACI 318: Ch. 16	—
10. Verification of in-situ concrete strength, prior to stressing of tendons in posttensioned concrete and prior to removal of shores and forms from beams and structural slabs.	—	X	ACI 318: 6.2	1906.2

For SI: 1 inch = 25.4 mm.

a. Where applicable, see also Section 1707.1, Special inspection for seismic resistance.

Arizona Residential Post-Tensioned Round Table  
March 2007

**Recommendations for Standards of Construction  
and Design #2**

**EVALUATION AND ACCEPTANCE OF CONCRETE**

The requirements for evaluation and acceptance of concrete are provided in Section 1905.6 of the 2003 International Building Code (IBC). There are no exceptions to these provisions. The Phoenix Post-Tensioned Round Table makes the following recommendations for evaluation and acceptance of concrete for residential post-tensioned slabs on ground.

Because of the large variations in slab thickness, slab size and scheduling of pours, the Arizona Residential Post-Tensioned Round Table recommends that cylinders be taken on every lot. This would satisfy the intent of the code and provide consistent documentation for the structural engineers and building officials.

It is recommended that a minimum of four cylinders be cast as a strength sampling for each lot. One cylinder for early strength testing, two cylinders to verify  $f'_c$  (1905.2.4), and the fourth cylinder for a 56-day strength break if required.

The information presented for Recommendations for Standards of Construction and Design and its interpretation is only advisory. Please consult your local municipality, building official and/or your Structural Engineer of Record. They shall have the authority to adopt policies and procedures in order to change or clarify the aforementioned recommendations. Any changes or interpretations should be validated by written documentation

Please see Appendix A, Recommendations for Standards of Construction and Design #2 for further information.

### **Code Reference: IBC 2003 Section 1905.6.2 Frequency of Testing**

The frequency of conducting strength tests of concrete shall be as specified in Section 1905.6.2.1 through 1905.6.2.4

#### **1905.6.2.1 Minimum Frequency**

Samples for strength tests of each class of concrete placed each day shall be taken not less than once a day, nor less than once for each 150 cubic yards of concrete, nor less than once for each 5000 square feet of surface area for slabs or walls.

#### **1905.6.2.2 Minimum Number**

On a given project, if the total volume of concrete is such that the frequency of testing required by Section 1905.6.2.1 would provide less than five strength tests for a given class of concrete, tests shall be made from at least five randomly selected batches or from each batch if fewer than five batches are used.

#### **1905.2.3 Small Volume**

When the total volume of a given class of concrete is less than 50 cubic yards strength tests are not required when evidence of satisfactory strength is submitted to and approved by the building official.

#### **1905.2.4 Strength Test**

A strength test shall be the average of the strength of two cylinders made from the same sample of concrete and tested at 28 days or at the test age designated for the determination of  $f'_c$ .

The parameters stated in 1905.6.2.1 are very specific. We have observed that PT slabs vary in thickness from 6" to 10". For an average 1800 square foot house the concrete yardage could vary from 34 cubic yards for a 6" thick slab to 56 cubic yards for a 10" thick slab. In the larger home communities with an average 2500 square foot house, the range could be between 46-78 cubic yards. It is not uncommon to see houses on the same tract with different slab thicknesses as well as large variations in square footage. There are larger slabs that require over 120 cubic yards of concrete due to size and thickness.

The requirement states in 1905.6.2.1 that cylinders must be taken at least once a day, or every 150 yards or every 5000 square feet. Collecting all of the information to meet these three criteria with the wide variety of design specifications, variety of sizes of slabs in a given subdivision and the imprecise nature of pour schedules creates considerable tracking issues. It is the position of the Arizona Residential Post-Tension Round Table that cylinders are taken on every lot. This procedure ensures that a record of concrete strength is provided for each post-tensioned slab and satisfies the intent of the code.



People Helping People Build a Safer World™

Chicago District Office

4051 W. Flossmoor Road ■ Country Club Hills, IL 60478-5795 U.S.A.  
Tel: +1 (708) 799-2300 ■ Fax: +1 (708) 799-4981  
Toll Free: +1-888-ICC-SAFE (422-7233)

www.iccsafe.org

PRESIDENT  
**HENRY L. GREEN**  
Executive Director  
Bureau of Construction Codes & Fire Safety  
Michigan Dept. of Labor & Economic Growth  
Lansing, Michigan

VICE PRESIDENT  
**WALLY BAILEY, C.B.O.**  
Director, Development  
and Construction  
Ft. Smith, Arkansas

SECRETARY/TREASURER  
**STEVEN I. SHAPIRO, C.B.O.**  
Director of Codes Compliance  
Hampton, Virginia

IMMEDIATE PAST PRESIDENT  
**FRANK P. HODGE, JR., C.B.O., M.C.P.**  
Director of Building and  
Fire Codes  
Hilton Head Island, South Carolina

**EDWIN M. BERKEL, C.F.I.**  
Fire Marshal  
Mehlville Fire Protection District  
St. Louis, Missouri

**JAMES L. BROTHERS**  
Building Director  
Decatur, Alabama

**TERRENCE L. COBB, C.B.O.**  
Director, Dept. of Codes Administration  
Nashville/Davidson County, Tennessee

**JOHN DARNALL, C.B.O.**  
Assistant Director of  
Development Services  
Tumwater, Washington

**WILLIAM L. DUCK, JR., C.B.O.**  
Director, Dept. of  
Inspections and Code  
Columbus, Georgia

**WILLIAM D. DUPLER**  
Building Official  
Chesterfield, Virginia

**GERALD D. GEORGE, C.B.O.**  
Chief Building Official  
Boulder County, Colorado

**GREG JOHNSON**  
Building Inspector  
Saint Paul, Minnesota

**JOHN T. LaTORRA**  
Building & Inspection Manager  
Redwood City, California

**RONALD L. LYNN**  
Building Official  
Clark County, Nevada

**RONALD E. PIESTER, R.A.**  
Director, Division of  
Code Enforcement and Administration  
State of New York  
Albany, New York

**JAMES T. RYAN, C.B.O.**  
Codes Administrator  
Overland Park, Kansas

**KEVIN H. SCOTT**  
Deputy Fire Chief  
of Kern County  
Bakersfield, California

**ADOLF A. ZUBIA**  
Fire Chief  
Las Cruces, New Mexico

CHIEF EXECUTIVE OFFICER  
**JAMES L. WITT**

December 8, 2005

Mr. Brian Juedes, P.E., S.E., Architect  
Felten Group, Inc.  
3602 East Greenway Road  
Suite #107  
Phoenix, AZ 85032

**RE: Sections 101.2, 1704.1, 1704.4, 1905.1 and 1905.6 of the  
ICC International Building Code/2003**

Dear Mr. Juedes:

On December 6, 2005 we received your fax transmittal of December 5th concerning special inspections along with the evaluation and acceptance criteria for concrete construction. Our answers to your letter are contained herein and are based on the above referenced code sections.

We understand your situation involves a residential reinforced concrete slab-on-grade that has been designed and post-tensioned for the expansive soils located below the building. You are specifically asking whether special inspections are required for this concrete construction. The answer is Yes.

Special inspections are required by the code for those large complex projects involving structural materials with highly detailed critical connections. The adequacy of structural members, materials and components along with the construction work needed to assemble those items must be carefully inspected to verify compliance with not only the building code but also its referenced standards. Exception No. 3 of Section 1704.4 exempts special inspections for nonstructural concrete slabs poured directly onto grade such as driveways, patios, basement slabs, floor slabs, etc. since the uniformly distributed live loads are transferred directly into the underlying soils. In your specific situation, a post-tensioned concrete floor slab designed and constructed to resist the uplift forces of expansive soils is no longer a nonstructural component and must be specially inspected.

Headquarters: 5203 Leesburg Pike, Suite 600 ■ Falls Church, VA 22041-3405 U.S.A.

Tel: +1 (703) 931-4533 ■ Fax: +1 (703) 379-1546

Toll Free: +1-888-ICC-SAFE (422-7233)



People Helping People Build a Safer World™

Chicago District Office  
4051 W. Flossmoor Road ■ Country Club Hills, IL 60478-5795 U.S.A.  
Tel: +1 (708) 799-2300 ■ Fax: +1 (708) 799-4981  
Toll Free: +1-888-ICC-SAFE (422-7233)

[www.iccsafe.org](http://www.iccsafe.org)

December 8, 2005

Page 2

You have also asked whether concrete construction is still subject to the evaluation and acceptance criteria of Section 1905.6 even if it is exempt from the special inspection requirements of Section 1704.4. The answer is Yes. The provisions of Section 1905 provide methods for testing concrete and criteria for its evaluation and acceptance based on strength requirements. There are no exceptions to these provisions listed directly in Section 1905.6.

As an important side note, both your letter and recent phone conversation with our Mr. Allan Bilka indicated this slab was for a residential project. Please keep in mind that all detached single-family houses, detached simple duplexes and townhouses are required to be regulated and constructed in accordance with the ICC International Residential Code.

We hope this answers your letter in full. If you have any further questions, please call. These opinions are based on the information which you have provided. We have made no independent effort to verify the accuracy of your submitted information nor have we conducted a review beyond the scope of your questions. As this interpretation is only advisory, please consult with the authority having jurisdiction, the building official.

Very truly yours,

A handwritten signature in black ink, appearing to read "Gary L. Nelson".

Gary L. Nelson, P.E.  
Senior Staff Engineer

cc: Mr. Allan Bilka - ICC Chicago District Office



People Helping People Build a Safer World™

Chicago District Office
4051 W. Flossmoor Road ■ Country Club Hills, IL 60478-5795 U.S.A.
Tel: +1 (708) 799-2300 ■ Fax: +1 (708) 799-4981
Toll Free: +1-888-ICC-SAFE (422-7233)

www.iccsafe.org

PRESIDENT
HENRY L. GREEN
Executive Director
Bureau of Construction Codes & Fire Safety
Michigan Dept. of Labor & Economic Growth
Lansing, Michigan

VICE PRESIDENT
WALLY BAILEY, C.B.O.
Director, Development
and Construction
Ft. Smith, Arkansas

SECRETARY/TREASURER
STEVEN I. SHAPIRO, C.B.O.
Director of Codes Compliance
Hampton, Virginia

IMMEDIATE PAST PRESIDENT
FRANK P. HODGE, JR., C.B.O., M.C.P.
Director of Building and
Fire Codes
Hilton Head Island, South Carolina

EDWIN M. BERKEL, C.F.I.
Fire Marshal
Mehlville Fire Protection District
St. Louis, Missouri

JAMES L. BROTHERS
Building Director
Decatur, Alabama

TERRENCE L. COBB, C.B.O.
Director, Dept. of Codes Administration
Nashville/Davidson County, Tennessee

JOHN DARNALL, C.B.O.
Assistant Director of
Development Services
Tumwater, Washington

WILLIAM L. DUCK, JR., C.B.O.
Director, Dept. of
Inspections and Code
Columbus, Georgia

WILLIAM D. DUPLER
Building Official
Chesterfield, Virginia

GERALD D. GEORGE, C.B.O.
Chief Building Official
Boulder County, Colorado

GREG JOHNSON
Building Inspector
Saint Paul, Minnesota

JOHN T. LaTORRA
Building & Inspection Manager
Redwood City, California

RONALD L. LYNN
Building Official
Clark County, Nevada

RONALD E. PIESTER, R.A.
Director, Division of
Code Enforcement and Administration
State of New York
Albany, New York

JAMES T. RYAN, C.B.O.
Codes Administrator
Overland Park, Kansas

KEVIN H. SCOTT
Deputy Fire Chief
of Kern County
Bakersfield, California

ADOLF A. ZUBIA
Fire Chief
Las Cruces, New Mexico

CHIEF EXECUTIVE OFFICER
JAMES L. WITT

March 27, 2006

Mr. Brian Juedes, P.E., S.E.,
Felten Group
3602 E. Greenway
Suite 107
Phoenix, AZ 85032

RE: Table 1704.4 of the 2003 International Building Code

Dear Mr. Juedes:

This letter is in response to your letter, dated February 9, 2006, faxed to this office.

Your question was: Table 1704.4 Item 5 indicates "continuous inspection" at the time fresh concrete is sampled..." does this mean the Special Inspector need only be on site when the concrete is sampled or should the Special Inspector be on site for the full duration of the concrete pour?

My answer is that the column under "continuous" is indicated here because test samples are to be taken at periodic points throughout the placement of the concrete. Therefore, an inspector must be available continuously to verify that this is being done. Please note that there are other inspections that will also require continuous presence during a concrete lift.

This opinion is based on the information which you have provided. We have made no independent effort to verify the accuracy of your submitted information nor have we conducted a review beyond the scope of your question. As this interpretation is only advisory, please consult with the authority having jurisdiction, the code official.

I hope this letter assists you. If you have any questions or comments, please do not hesitate to contact me.

Very truly yours,

[Handwritten signature of David A. Bowman]

David A. Bowman
Manager, Code Development

Headquarters: 5203 Leesburg Pike, Suite 600 ■ Falls Church, VA 22041-3405 U.S.A.
Tel: +1 (703) 931-4533 ■ Fax: +1 (703) 379-1546
Toll Free: +1-888-ICC-SAFE (422-7233)