



MARICOPA COUNTY
Department of Transportation

MEMORANDUM

Date: May 12, 2009
To: MAG Specifications and Details Committee
From: Robert Herz, MCDOT Representative
Subject: Miscellaneous Bloopers Case 09-A

PURPOSE: Correct typographical errors.

REVISION: Change the table reference shown in the last paragraph of section 321.10.4 prior to Table 321-6 from Table 321-2 to Table 321-6 as indicated below.

If the pavement thickness deficiency is greater than 0.25 inches and the contracting agency is the owner, Table 321-6 will apply.

Deleted: 321-2

TABLE 321-6	
ASPHALT PAVEMENT THICKNESS PAYMENT REDUCTION	
For Thickness Deficiency of More Than 0.25 inches and less than 0.50 inches	
Specified Mat Thickness	Reduction in Payment or Corrective Action
Less than 1.5 inches	50%
1.50 inches to 1.99 inches	33%
2.00 inches to 2.49 inches	25%
2.50 inches to 2.99 inches	20%
3.00 inches and over	17%

321.10.5 Density: Achieving the required compaction is the responsibility of the contractor. The number and types of rollers is the contractor's responsibility and shall be sufficient to meet these requirements.



MARICOPA COUNTY
Department of Transportation

MEMORANDUM

Date: July 1, 2009
To: MAG Specifications and Details Committee
From: Robert Herz, MCDOT Representative
Subject: Miscellaneous Bloopers **Case 09-12 B**

PURPOSE: Correct typographical error.

REVISION: Correct the table value for the percent passing the #30 sieve in section 325.2.1.

325.2.1 AGGREGATE:

The aggregate shall meet the following gradation:

<u>Sieve Size</u>	<u>Percent Passing</u>
1/2 inch	100
3/8 inch	78-92
#4	28-42
#8	15-25
#30	5-15
#200	3-7

Deleted: 15-24

SECTION 715

TABLE 715-1			
SLURRY SEAL AGGREGATE			
SIEVE SIZE	Type I % PASSING	Type II % PASSING	Type III % PASSING
38053	100	100	100
No. 4	100	85/100	70/90
No. 8	90/100	65/90	45/70
No. 16	65/90	45/70	28/50
No. 30	40/60	30/50	19/34
No. 50	25/42	18/30	38345
No. 100	15/30	38280	38185
No. 200	38279	38121	38121
Emulsified Asphalt content as a % of Dry Wt. Of Aggregate (approx.) ASTM D-3910 (W.T.A.T. TEST)	18	16	14
Residual Asphalt Range requirements % of Dry Wt. of Aggregate ASTM D-3910 (W.T.A.T. TEST)	38275	7.5-13	6.5-12
Pounds of Aggregate per Square Yard (approx.)	38208	38338	18-25

End of Section

2005 MAG

CASE 09-12C

SECTION 715

TABLE 715-1			
SLURRY SEAL AGGREGATE			
SIEVE SIZE	Type I % PASSING	Type II % PASSING	Type III % PASSING
3/8	100	100	100
No. 4	100	85/100	70/90
No. 8	90/100	65/90	45/70
No. 16	65/90	45/70	28/50
No. 30	40/60	30/50	19/34
No. 50	25/42	18/30	12/25
No. 100	15/30	10/21	7/18
No. 200	10/20	5/15	5/15
Emulsified Asphalt content as a % of Dry Wt. Of Aggregate (approx.) ASTM D-3910 (W.T.A.T. TEST)	18	16	14
Residual Asphalt Range requirements % of Dry Wt. of Aggregate ASTM D-3910 (W.T.A.T. TEST)	10-16	7.5-13	6.5-12
Pounds of Aggregate per Square Yard (approx.)	8-10	12-18	18-25

End of Section